



Ami Polymer Pvt. Ltd.

Chemical Resistance – Imaprene™ Tubing

Acetaldehyde	E	Aniline Oil	G	Butyl Alcohol	E	Chromic Acid	G
Acetic Acid, 10%	E	Animal Fats	G	Butyl Aldehyde	E	Chromium Trioxide	G
Acetic Acid, 50%	E	Antmony Pentachloride	E	Butyl Bezyll Phthalate	G	Cinnamene	-
Acetic Acid, Glacial	E	Aqua Regia	F	Butyl Carbitol	C	Cis-9-Octadecenoic Acid	G
Acetic Anhydride	E	Argon	E	Butyl Cellusolve	E	Citric Acid	E
Acetic Oxide	E	Arsenic Acid	E	Butyl Chloride	G	Coal Oil	X
Acetone	E	Asphalt	F	Butyl Ether	G	Coal Tar	F
Acetone Cyanohydrin	E	ASTM Fuel A	F	Butyl Ether Acetaldehyde	G	Coal Tar Naphtha	F
Acetonitrile	E	ASTM Fuel B	C	Butal Ethyl Ether	F	Coconut Oil	G
Acetophenone	G	ASTM Fuel C	C	Butyl Oleate	G	Coke Oven Gas	F
Acetyl Acetone	E	ASTM Oil No. 1	F	Butyl Phthalate	G	Coolanol (Monsanto)	X
Acetyl Chloride	X	ASTM Oil No. 2	X	Butyl Stearate	G	Copper Chloride	C
Acetyl Oxide	E	ASTM Oil No. 3	X	Butylene	F	Copper Cyanide	C
Acetylene	E	ASTM Oil No. 4	X	Butyraldehyde	E	Copper Hydrate	C
Acetylene DI + Tetra Chloride	X	Automatic Transmission Fluid	X	Butyric Acid	E	Copper Hydroxide	C
Acrolein	E	Banana Oil	G	Butyric Anhydride	E	Copper Sulfate	C
Acrylonitrile	X	Barium Chloride	E	Cadmium Acetate	E	Corn Oil	G
Acrylic Acid	E	Barium Hydroxide	E	Calcium Acetate	E	Cottonseed Oil	G
Air +300F	X	Barium Sulfide	E	Calcium Aluminate	E	Creosote	G



Ami Polymer Pvt. Ltd.

Alk-Tri	-	Beer	E	Calcium Bichromate	E	Cresols	G
Allyl Alcohol	E	Beet Sugar Liquors	E	Calcium Bisulfide	C	Cresylic Acid	G
Allyl Bromide	F	Benzel Chloride	C	Calcium Chloride	E	Crotonaldehyde	E
Allyl Chloride	F	Benzaldehyde	G	Calcium Hydroxide	E	Crude Oil	C
Alum	E	Benzene	X	Calcium Hypochlorite	G	Cumene	X
Aluminum Acetate	E	Benzene Carboxylic Acid	E	Calcium Nitrate	E	Cupric Carbonate	E
Aluminum Chloride	E	Benzine	X	Calcium Sulfide	E	Cupric Hydroxide	E
Aluminum Flouride	E	Benzoic Acid	E	Caprylic Acid	G	Cupric Nitrate	E
Aluminum Formate	E	Benzol	X	Carbamide	E	Cupric Sulfate	E
Aluminum Hydroxide	E	Benzotrichloride	X	Carbitol	E	Cutting Oil	C
Aluminum Nitrate	E	Benzyl Acetate	F	Carbolic Acid Phenol	F	Cyclohexane	X
Aluminum Sulfate	E	Benzyl Alcohol	F	Carbon Dioxide	E	Cyclohexanol	G
Alums-NH3 CR K	E	Benzyl Chloride	F	Carbon Disulfide	X	Cyclohexanone	G
Amines - Mixed	G	Benzyl Ether	X	Carbon Monoxide	E	Cyclopentane	C
Aminobenzene	E	Bis (2-Chloroethyl) Ether	C	Carbon Tetrachloride	X	Cyclopentanol	G
Aminodimethylbenzene	F	Black Sulfate Liquor	E	Carbonic Acid	E	Cyclopentanone	G
Aminoethane	E	Bleach	G	Castrol Oil	G	Cyclopentil Alcohol	G
Aminoxilene	F	Borax Solution	E	Caustic Sode (See Sodium Hydroxide)	E	D-Furaldehyde	G
Ammonium Carbonate	E	Boric Acid	E	Cellosolve Acetate	E	DDT in Kerosene	X



Ami Polymer Pvt. Ltd.

Ammonium Chloride	E	Brake Fluid (HD-557) 12 Days	F	Celluguard	-	Decahydronaphtalene	X
Ammonium Hydroxide	E	Brine	E	Cetylic Acid	G	Decahydroxnaphtalene	X
Ammonium Nitrate	E	Bromacil	-	China Wood Oil (Tung Oil)	-	Decalin	X
Ammonium Phosphate, Dibasic	E	Bromobenzene	X	Chlorinated Solvents	X	Decyl Alcohol	G
Ammonium Sulphate	E	Bromochlorometane	F	Chloro-2-Propane	F	Decyl Aldehyde	G
Ammonium Sulphite	E	Bromomethane	F	Chloroacetic Acid	X	Decyl Butyl Phthalate	F
Ammonium Thiosulfate	E	Bromotoluene	X	Chloroacetone	G	Decyl Carbinol	F
Amyl Acetate	X	Bugdioxine	-	Chlorobenzene	X	Detergent, Water Solution	E
Amyl Acetone	F	Bunker Oil	-	Chlorobutane	G	Developing Fluid (Photo)	G
Amyl Alcohol	E	Butaoiene	C	Chlorodane	G	Dextron	E
Amyl Bromide	F	Butane	C	Chloroethyl Benzene	X	Di (2ethylhexyl) Adipate	G
Amyl Chloride	X	Butanoic Acid	E	Chloroform	X	Di (2ethylhexyl) Phthalate	F
Amyl Ether	F	Butanol (Butyl Alcohol)	E	Chloropentane	F	Di-Iso-Butylene	X
Amylamine	F	Butanone	E	Chlorosulfonic Acid	G	Di-Iso-Decyl Phthalate	G
Anethole	C	Butoxyethanol	E	Chlorotoluene	F	Di-Iso-Propanolamine	G
Aniline	E	Butyl Acetate	X	Chlorox	G	Di-Iso-Propyl Ether	F
Aniline Dyes	E	Butyl Acrylate	X	Chrome Plating Solutions	E	Di-Iso-Propyl Ketone	F



Ami Polymer Pvt. Ltd.

Di-P-Mentha-1, 8 Diene	X	Dimethyl Sulfide	G	Ethylene Chlorohydrin	E	Heptane	X
Diacetone Alcohol	E	Dimethyl-3-Pentanone	F	Ethylene Diamine	E	Heptane Carboxylic Acid	G
Diacetylmethane	G	Dimethyl-4-Heptanone	F	Ethylene Dibromide	C	Heptanoic Acid	G
Diallylphthalate	G	Dimethylamine	E	Ethylene Dichloride	C	Heptanone	F
Diammonium Phosphate	E	Dimethylaniline	G	Ethylene G Monobutyl Ether	G	Hexadecanoic Acid	F
Diamyl Naphthalene	X	Dimethylbenzene	X	Ethylene G Monoethyl Ether	G	Hexaldehyde	G
Diamylamine	G	Dimethylbutane	C	Ethylene G Monoethyl E Acetate	G	Hexane	X
Diamylene	F	Diocetyl Adipate	F	Ethylene G Monoethyl Ether	-	Hexanol	G
Diamylphenol	F	Diocetyl Phthalate	G	Ethylene Glycol	E	Hexene	C
Dibenzyl Ether	F	Dioxalane	G	Ethylene Oxide	E	Hexyl Alcohol	G
Dibromobenzene	X	Dioxane	G	Fatty Acids	G	Hexyl Methyl Ketone	F
Dibromomethane	-	Dipentene	F	Ferric Bromade	E	Hexilamine	G
Dibutyl Ether	G	Dipentylamine	F	Ferric Chloride	E	Hexylene Glycol	E
Dibutyl Phthalate	G	Diproylamineolamine	G	Ferric Nitrate	E	Histowax	-
Dibutyl Sebacate	G	Dipropylene Glycol	E	Ferric Sulfate	E	Hydraulic Motor Oil	C
Dibutylamine	G	Disodium Phosphate	E	Ferrous Acetate	E	Hydrazine	E
Dicalcium Phosphate	E	Divinyl Benzene	X	Ferrous Chloride	E	Hydrobromic Acid	E
Dichloroethylene	F	Dowell Inhibitor	-	Ferrous Sulfate	E	Hydrocyanic Acid	E
Dichloroacetic Acid	E	Dowfax 2A1 Solvent	-	Fluoboric Acid	E	Hydrochloric Acid	E
Dichlorobenzene	F	Dowfax 2A1 TA	-	Fluorine	X	Hydroflouric Acid	X
Dichlorobutane	F	Dowfax 6A1	-	Fluosilicic Acid	E	Hydrogen	E



Ami Polymer Pvt. Ltd.

		Solvent				Chloride Anhydrous	
Dichlorodifluoromethane	X	Dowfax 6A1 TA	-	Formaldehyde	E	Hydrogen Dioxide (10%)	-
Dichloroethane	F	Dowthermn, A and E	-	Formalin	E	Hydrogen Gas	E
Dichloroethyl Ether	F	Dry Cleaning Fluids	X	Formic Acid	E	Hydrogen Peroxide 10%	G
Dichlorohexane	F	Ducgkirioebaane	-	Freon 113	X	Hydrogen Peroxide over 10%	F
Dichloromethane	F	Duro AW-16, 31	-	Freon 12	X	Hydrogen Sulfide (wet)	E
Dichloropentane	F	Duro FR-HD	-	Freon 22	X	Hydroxy Benzene	F
Dichloropropane	F	Ethanoic Acid	E	Freon so2	X	Hydroxyisobutyro nirile	E
Dichloropropene	F	Ethanol (Grain Alcohol)	-	Fuel A (ASTM)	F	Hydroxytoluene	F
Dichlorotoluene	F	Ethanolamine	E	Fuel B (ASTM)	C	Hyvar XL	-
Diesel Oil	F	Ethers	G	Fuel Oil	X	Iminodi-1-Propanol	G
Diethanol Amine	G	Ethyl Acetate	E	Furan	F	Iminodiethanol	G
Diethyl Ether	G	Ethyl Acetoacetate	E	Furfural	G	Iodine	E
Diethyl Ketone	G	Ethyl Acetone	E	Furfuran	F	Iodine Pentafluoride	X
Diethyl Oxalate	G	Ethyl Acrylate	E	Furfuryl Alcohol	G	Iodoform	G
Diethyl Phthalate	G	Ethyl Alcohol	E	Gallic Acid	G	Iso-Butanal	G
Diethyl Sebacate	G	Ethyl Aldehyde	E	Gallotanic Acid	-	Iso-Butylamine	G
Diethyl Sulfate	E	Ethyl Aluminium Dichloride	E	Gas, Coal	C	Iso-Butylbromide	F
Diethylamine	E	Ethyl Benzene	X	Gas, High Octane	C	Isobutylcarbinol	G
Diethylbenzene	X	Ethyl Bromide	F	Gasoline	X	Iso-Octane	X
Diethylene Glycol	E	Ethyl Butyl Acetate	-	Glacial Acrylic Acid	E	Isocyanates	G
Diethylene Oxide	E	Ethyl Butyl Alcohol	-	Gluconic Acid	E	Isooctane	X



Ami Polymer Pvt. Ltd.

Diethylenetriamine	E	Ethyl Cellulose	E	Glucose	E	Isopropyl Acetate	
Diethylamine	E	Ethyl Chloride	F	Glycerine	E	Isopropyl Alcohol	E
Dihydroxy Diethyl Ether	E	Ethyl Di-isobutylthio-Carbamate	E	Glycerol	E	Isopropyl Ether	F
Dihydroxy Succinic Acid	E	Ethyl Dichloride	X	Glycogenic Acid	G	Jet Fuels	X
Dihydroxydiethyl Ether	E	Ethyl Ether	G	Glycols	E	Jp-4 Oil	X
Diisobutyl Ketone	F	Ethyl Formate	E	Glyconic Acid	E	Kerosene	X
Diisodecyl Phthalate	F	Ethyl Iodide	G	Glycyl Alcohol	E	Ketones	C
Diisooctyl Adipate	F	Ethyl Oxalate	E	Grease	F	Lacquer Solvents	X
Diisooctyl Phthalate	F	Ethyl Phthalate	G	Green Sulphate Liquor	E	Lactic Acid - Cold	E
Dimethyl Carbinol	E	Ethyl Silicate	E	Halon 1211	-	Lactic Acid - Hot	E
Dimethyl Ketone	G	Ethyl-1-Butanol	G	Helium	E	Lard	G
Dimethyl Phthalate	G	Ethyl-N-Butyl Ketone	G	Heptaldehyde	G	Lavender Oil	F
Dimethyl Sulfate	G	Ethylamine	G	Heptanal	G	Lead Acetate	

Lead Nitrate	E	Methyl Propyl Ether	G	Mil-L-21260	-	Nickel Sulfate	E
Lead Sulfate	E	Methyl Salicylate	G	Mil-L-23699	-	Nietylene	-
Lime	E	Methyl Styrene	X	Mil-L-25681	-	Nitric Acid, 10%	E
Lime Bleach	E	Methyl Sulfide	G	Mil-L-3150	-	Nitric Acid, 13n	X
Lime Sulfur	E	Methyl Tertiary Butyl Ether	F	Mil-L-4343	-	Nitric Acid, 13n + 5%	X
Limonene	X	Methyl-2-Butanol	G	Mil-L-6082	-	Nitric Acid, 20%	E
Linoleic Acid	F	Methyl-2-Butanone	G	Mil-L-6085	-	Nitric Acid, 30%	G



Ami Polymer Pvt. Ltd.

Linseed Oil	F	Methyl-2-Hexanone	F	Mil-L-7808	-	Nitric Acid, 30%-70%	F
Liquid Petroleum Gas (LPG)	X	Methyl-2-Pentanol	G	Mil-L-7870	-	Nitric Acid, Conc (16n)	X
Lubricating Oils	X	Methyl-2-Pentanone	F	Mil-L-9000	-	Nitric Acid, Red Fuming	X
Lye Solutions	G	Methyl-2-Propen-L-OI	-	Mil-L-9236	-	Nitrilotriethanol	E
Magnesium Acetate	E	Methyl-3-Penten-1-One	F	Mil-P-27402	-	Nitrobenzene	X
Magnesium Chloride	E	Methyl-4-Isopropyl Benzene	X	Mil-R-25576 (RP-1)	-	Nitroethane	E
Magnesium Hydrate	E	Methyl-Iso-Amyl-Ketone	F	Mil-S-3136 Type 1 Fuel	-	Nitrogen	E
Magnesium Hydroxide	E	Methyl-L-Propanol	E	Mil-S-3136 Type 2 Fuel	-	Nitromethane	E
Magnesium Sulfate & Sulphite	E	Methylallyl Acetate	G	Mil-S-3136 Type 3 Fuel	-	Nitrous Oxide Gas	E
Maleic Acide	E	Methylamyl Alcohol	G	Mil-S-3136 Type 4 Oil, Low Swell	-	Nonanoic Acid	G
Maleic Anhydride	E	Methylcyclohexane	X	Mil-S-3136 Type 5 Oil, Med Swell	-	Nonanol	G
Malic Acid	E	Methylene Bromide	F	Mil-S-3136 Type 6 Oil, Hi. Swell	-	Nuto H	-
Manganous Sulfate	E	Methylene Chloride	F	Mil-S-81087	-	Nyvac Light	-
Mapp	G	Methylethyl Ketone	E	Mineral Oil	F	Octanoic Acid	G
Mek	E	Methylhexyl Ketone	F	Mineral Spirits	F	Octanol	G
Mercury	E	Methylisobutyl Carbinol	G	Mobile HFA	X	Octyl Acetate	G
Mercury Vapours	E	Methylisobutyl Ketone	G	Molten Sulfur	G	Octyl Alcohol	G
Mesityl Oxide	F	Methylisopropyl Ketone	G	Mono-Chloroacetic Acid	E	Octyl Aldehyde	G
Methallyl Chloride	G	Methylactonitrile	E	Monobutyl Ether	G	Octyl Amine	G



Ami Polymer Pvt. Ltd.

Methane Carboxylic Acid	E	Methylphenol	G	Monochlorobenzene	X	Octyl Carbinol	G
Methanoic Acid	E	Methylpropyl Carbinol	E	Monochlorodifluoromethane	G	Octylene Glycol	G
Methanol (Methyl Alcohol)	E	Methylpropyl Ketone	G	Monoethanol Amine	E	Oil-Petroleum	X
Methanol (Wood Alcohol)	E	Mil-A-6091	-	Monoethyl Amine	E	Oleic Acid	F
Methoxy Ethanol	E	Mil-C-4339	-	Monoethylamine	E	Oleum (Fuming Sulfuric Acid)	X
Methoxyethoxy Ethanol	E	Mil-C-7024	-	Morpholine	E	Olive Oil	G
Methoxypropenyl Benzene	F	Mil-E-9500	-	Motor Oil, 40W	C	Orth-Dichlorobenzene	F
Methyl 1-2, 4-Pentenediol	E	Mil-F-16884	-	MTBE	G	Ortho-Dichlorobenzol	F
Methyl Acetate	E	Mil-F-17111	-	Muriatic Acid	E	Orthoxylene	X
Methyl Acetoacetate	E	Mil-F-25558 (Rj-1)	-	N-Butanal	E	Oxalic Acid	E
Methyl Acetone	G	Mil-G-10924	-	N-Butylamine	E	Oxydiethanol	E
Methyl Acetylene Propadiene	C	Mil-G-25013	-	N-Butylbenzene	X	Ozone	E
Methyl Alcohol	E	Mil-G-25537	-	N-Butylbromide	F	P-Cymene	X
Methyl Allyl Alcohol	E	Mil-G-3545	-	N-Butylbutyrate	G	Paint Thinner	X
Methyl Allyl Chloride	G	Mil-G-5572	-	N-Butylcarbinol	E	Palmatic Acid	E
Methyl Amyl Carbinol	G	Mil-G-7711	-	N-Nonyl Alcohol	G	Papermakers Alum	E
Methyl Benzene	X	Mil-H-05606 (HFA)	-	N-Octane	X	Para-Dichlorobenzene	F
Methyl Bromide	C	Mil-H-13910	-	N-Serv (75% Xylene)	X	Paraffin Wax	G
Methyl Butane	C	Mil-H-19457	-	Na-K	-	Paraldehyde	G
Methyl Butyl Alcohol	G	Mil-H-22251	-	Naphtha	X	Paraxylene	X
Methyl Butyl	G	Mil-H-27601	-	Naphthalene	F	PCB	X



Ami Polymer Pvt. Ltd.

Ketone							
Methyl Carbitol	-	Mil-H-5606 (j43)	-	Naphthenic Acids	F	Pelargonic Alcohol	G
Methyl Cellosolve	E	Mil-H-6083	-	Natural Gas	G	Pentachloroethane	X
Methyl Chloride	G	Mil-H-8446 (MLO-8515)	-	Neohexane	C	Pentadione	F
Methyl Cyanide	E	Mil-J-5161	-	Neon Gas	E	Pentamethylene	F
Methyl Ethil Ketone	E	Mil-J-5624 (Jp-3, Jp-4, Jp-5)	-	Neu-Tri	-	Pentane	F
Methyl Hexanol	G	Mil-L-15016	-	Nickel Acetate	E	Pentanol	G
Methyl Methacrylate	G	Mil-L-17331	-	Nickel Chloride	E	Pentanone	F
Methyl Normal Amyl Ketone	F	Mil-L-2104	-	Nickel Nitrate	E	Pentanol	-



Ami Polymer Pvt. Ltd.

Pentyl Acetate	G	Propanetriol	E	Sodium Dichromate	E	Tetrachloromethane	X
Pentyl Alcohol	G	Propanol	E	Sodium Hydrate	E	Tetrachloronaphthalene	X
Pental Bromide	F	Propanolamine	E	Sodium Hydrochlorite	G	Tetraethylene Glycol	G
Pentyl Chloride	F	Propanone	G	Sodium Hydroxide (Caustic Soda)	E	Tetraethylorthosilicate	G
Pentyl Ether	G	Propen-L-ol	E	Sodium Hypochlorite	C	Tetrahydrofuran	F
Pentylamine	E	Propenediamene	E	Sodium Metaphosphate	E	Thf	F
Perchloric Acid-2N	E	Propenenitrile	E	Sodium Nitrate	E	Tine Chloride	E
Perchloroethylene	X	Propenyl Alcohol	E	Sodium Perborate	E	Titanium Tetrachloride	G
Perchloromethane	X	Propenylanisole	F	Sodium Peroxide	E	Toluene	X
Petroleum Crude	X	Propionic Acid	E	Sodium Phosphate	E	Toluidine	X
Petroleum Ether	X	Propyl Acetate	E	Sodium Silicate	E	Toluol	X
Petroleum Oils	X	Propyl Alcohol	E	Sodium Sulfate	E	Transformer Oil	X
Phenbo	-	Propyl Aldehyde	E	Sodium Sulfide	E	Transmission 'A' Oil	X
Phenol	F	Propyl Benzene	X	Sodium Sulfite	E	Tri (2-Hydroxyethyl) Amine	F
Phenolsulfonic Acid	X	Propyl Chloride	F	Sodium Thiosulfate	E	Tributyl Phosphate	E
Phenylamine	E	Propyl Ether	G	Soybean Oil	G	Tributylamine	G
Phenylbromide	X	Propyl Nitrate	G	Stannic Chloride	E	Trichloroacetic Acid	E
Phenylbutane	X	Propylene	X	Stannic Sulfide	E	Trichlorobenzene	X
Phenylchloride	X	Propylene Diamine	G	Stannous Chloride	E	Trichloroethane	G
Phenylethylene	X	Propylene Glycol	E	Stannous Sulfide	E	Trichloroethylene	G
Phenylmethane	X	Pydraul, 'E' Series	-	Steam, below 350 F	X	Trichloromethane	X



Ami Polymer Pvt. Ltd.

Phenylmethanol	G	Pydraulic 'C'	-	Stearic Acid	E	Trichlorotoluene	X
Phenylmethyl Acetate	C	Quintoloric B22 Series	-	Stoddart Solvent	F	Tricresyl Phosphate	E
Phosphate Esters	E	Red Oil	-	Styrene	X	Triethanolamine	E
Phosphoric Acid 10%	E	Refrigerant 11	X	Sulfamic Acid	E	Triethylamine	E
Phosphoric Acid 10%-85%	E	Refrigerant 12	X	Sulfur	F	Triethylene Glycol	E
Phosphorus Trichloride	G	Refrigerant 22	X	Sulfur Chloride	G	Trihydroxybenzoic Acid	E
Picric Acid, h2O Solution	E	Resorcinol	E	Sulfur Dioxide	E	Trimethyl Pentanes (Mixed)	X
Pine Oil	X	Sae No.10 Oil	C	Sulfur Trioxide, Dry	E	Trimethyl Pentene	X
Pinene	X	Sal Ammoniac	E	Sulfuric Acid 60% (200 F)	E	Trimethylamine	E
Poly Chlorinated Biphenol	X	Sea Water	E	Sulfuric Acid, 25%	E	Trisodium Phosphate	E
Polyethylene Glycol E-400	E	Sewage	E	Sulfuric Acid, 25%-50%	G	Tritoyl Phosphate	G
Polyol Ester	F	Silicate Esters	E	Sulfuric Acid, 50%-96%	F	Tung Oil	C
Polypropylene Glycol	E	Silicate of Soda	E	Sulfuric Acid, Conc.	X	Tung Oil (China Oil)	C
Potassium Acetate	E	Silicone Grease	E	Sulfuric Acid, Fuming	X	Turpentine	X
Potassium Bisulfate	E	Silicone Oil	E	Sulfurous Acid, 10%	E	Udmh	-
Potassium Bisulfite	E	Silver Nitrate	E	Sulfurous Acid, 10%-85%	E	Undecyl Alcohol	F
Potassium Carbonate	E	Skidrol 500 Type 2	E	Sutan	-	Urea	E
Potassium Chloride	E	Skidrol 500b	E	T-Butyl Amine	G	Urethane Formulations	G
Potassium Chromate	E	Skidrol 500c	E	Tall Oil	F	Uric Acid	E



Ami Polymer Pvt. Ltd.

Potassium Cyanide	E	Skidrol 7000 Type 2	E	Tallow	G	Varnish	X
Potassium Dichromate	E	Soap Solutions	E	Tannic Acid	E	Vegetable Oils	G
Potassium Hydrate	E	Soda Ash	E	Tar	X	Versilibe f44	-
Potassium Hydroxide	E	Soda Lime	E	Tar Bituminous	X	Versilubr f55	-
Potassium Nitrate	E	Soda Niter	E	Tartaric Acid	E	Vinegar	E
Potassium Permanganate, 5%	E	Soda, Caustic	E	Telone 2	-	Vinegar Acid	E
Potassium Silicate	E	Sodium Acetate	E	Terpinol	G	Vinyl Acetate	E
Potassium Sulfate	E	Sodium Aluminate	E	Tertiary Butyl Alcohol	E	Vinyl Benzene	X
Potassium Sulfide	E	Sodium Bicarbonate	E	Tertiary Butyl Amine	E	Vinyl Chloride	G
Prestone Antifreeze	E	Sodium Bisulfite	E	Test Entry	-	Vinyl Ether	G
Priopionitrile	F	Sodium Borate	E	Test Entry 1	-	Vinyl Styrene	X
Producer Gas	X	Sodium Carbonate	E	Tetrachlorobenzen e	X	Vinyl Toluene	X
Propane	X	Sodium Chloride	E	Tetrachloroethane	X	Vinyl Trichloride	X
Propanediol	E	Sodium Cyanide	E	Tetrachloroethylen e	X	Vital, 4300, 5310	-



Ami Polymer Pvt. Ltd.

Vm & Naphtha	-	Zeolites	E	1-Bromobutane	F	2-Ethoxyethyl Acetate	E
Water	E	Zinc Carbonate	E	1-Chloro-2-Methyl Propane	F	2-Ethyl (Butyraldehyde)	G
Water, Boiling	E	Zinc Chloride	E	1-Chloro-3-Methyl Butane	F	2-Ethyl-1-Hexanol	E
Water, Soda	E	Zinc Chromate	E	1-Decanol	G	2-Ethylhexanoic Acid	G
Wemco C	-	Zinc Sulfate	E	1-Hendacanol	F	2-Ethylhexyl Acetate	G
Whisky	E	Zinc, Acetate	E	2 (2 Aminoethylamino) Ethanol	E	2-Octanone	F
White Oil	X	0-Aminotoluene	F	2 (2 Ethoxyethoxy) Ethanol	E	3-Bromopropene	F
White Pine Oil	X	1-Undecanol	F	2 (2 Ethoxyethoxy) Ethyl Acetate	E	3-Chloro-2-Methyl Propane	F
Wines	E	1,4-Dioxane	E	2, 4-Di-Sec-Pentylphenol	F	3-Chloropropene	F
Wood Alcohol	E	1-Amino 2 Propanol	E	2-Aminoethanol	E	30Al Oil	-
Wood Oil	G	1-Aminobutane	E	2-Chloro-1-Hydroxy-Benzene	F	4-Hydroxy-4-Methyl-2-Pentanone	F
Xenon	E	1-Aminopentane	G	2-Chlorophenol	F		
Xylene, Xylon	X	1-Bromo-3-Methyl Propane	F	2-Chloropropane	G		
Xylidine	-	1-Bromo-3-Methyl Butane	F	2-Ethoxyethanol	E		

Ratings: E = Excellent G = Good F = Fair X = Not Recommended

- This chemical compatibility chart is designed as General Guidelines. The rating mentioned against each chemical is based on data available from technical articles, rubber suppliers and technical advices.
- Many factors like service temperature, condition of usage, type of applications affect chemical compatibility of polymer.